

January, 2013

KOPELEN J-370

PP BLOCK COPOLYMER

General Information

Description

J-370 is impact block copolymer with ethylene content as co-monomer.

This grade is designed to be processed in conventional Injection molding equipment.

J-370 shows high melt flow and good balance of impact resistance and strength.

It has broad range of property, and is used from general supplies to automotive compound base resin.

Applications

- General supplies & Industrial supplies
- Automotive compound base resin

Physical Properties ¹				
Test Method	Nominal Values			
ASTM D1238	33	g/10min		
ASTM D792	0.90	g/cm ³		
ASTM D638	270	kgf/cm ²	27	MPa
ASTM D638	>50	%	>50	%
ASTM D790	14,000	kgf/cm ²	1,370	MPa
ASTM D256	6.0	kgf·cm/cm	58	J/m
ASTM D256	3.0	kgf-cm/cm	29	J/m
ASTM D648	105	${\mathbb C}$		
UL94	НВ			
	ASTM D1238 ASTM D792 ASTM D638 ASTM D638 ASTM D790 ASTM D256 ASTM D256 ASTM D256	Test Method ASTM D1238 33 ASTM D792 0.90 ASTM D638 270 ASTM D638 >50 ASTM D790 14,000 ASTM D256 6.0 ASTM D256 3.0 ASTM D648 105	Test Method Nominal Value ASTM D1238 33 g/10min ASTM D792 0.90 g/cm³ ASTM D638 270 kgf/cm² ASTM D638 >50 % ASTM D790 14,000 kgf/cm² ASTM D256 6.0 kgf·cm/cm ASTM D256 3.0 kgf·cm/cm	Test Method Nominal Values ASTM D1238 33 g/10min ASTM D792 0.90 g/cm³ ASTM D638 270 kgf/cm² 27 ASTM D638 >50 % >50 ASTM D790 14,000 kgf/cm² 1,370 ASTM D256 6.0 kgf·cm/cm 58 ASTM D256 3.0 kgf·cm/cm 29 ASTM D648 105 ℃

NOTE	ISO 9001, 14001,

¹ Physical Properties : these are not to be construed as specifications

/TS 16949



January, 2013

KOPELEN J-370

PP BLOCK COPOLYMER

General Information

Description

J-370 is impact block copolymer with ethylene content as co-monomer.

This grade is designed to be processed in conventional Injection molding equipment.

J-370 shows high melt flow and good balance of impact resistance and strength.

It has broad range of property, and is used from general supplies to automotive compound base resin.

Applications

- General supplies & Industrial supplies
- Automotive compound base resin

Physical Properties ¹				
Test Method	Nominal Values			
ISO 1133	33	g/10min		
ISO 1183	0.90	g/cm ³		
ISO 527-1	260	kgf/cm ²	25	MPa
ISO 527-1	<100	%	<100	%
ISO 178	12,000	kgf/cm ²	1,180	MPa
ISO 180	5.5	kgf·cm/cm	54	J/m
ISO 180	2.5	kgf-cm/cm	25	J/m
ISO 75-1	85	${\mathbb C}$		
UL94	НВ			
	Test Method ISO 1133 ISO 1183 ISO 527-1 ISO 527-1 ISO 178 ISO 180 ISO 180	Test Method ISO 1133 33 ISO 1183 0.90 ISO 527-1 260 ISO 527-1 <100 ISO 178 12,000 ISO 180 5.5 ISO 180 2.5	Test Method Nominal Value ISO 1133 33 g/10min ISO 1183 0.90 g/cm³ ISO 527-1 260 kgf/cm² ISO 527-1 <100	Test Method Nominal Values ISO 1133 33 g/10min ISO 1183 0.90 g/cm³ ISO 527-1 260 kgf/cm² 25 ISO 527-1 <100

NOTE	ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications