



### **Provisional**

1020FS20

# LOW DENSITY POLYETHYLENE FILM GRADE

1020FS20 is a film grade Low Density Polyethylene (LDPE). It contains slip additive. It can be processed easily on blown film lines.

## **TYPICAL CHARACTERISTICS\***

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE**
Density (23°C)	ASTM D 792	g/cc	0.920
Melt Flow Index (190°C / 2.16 Kg)	ASTM D 1238	g/10 min.	2.0
Tensile Strength at Break (MD / TD)	ASTM D 882	MPa	20.0 / 19.0
Elongation at Break (MD / TD)	ASTM D 882	%	275 / 425
Dart Impact Strength (F50)	ASTM D 1709/A	g / µm	3.0

<sup>\*</sup> Typical characteristics and not to be taken as specifications

#### **APPLICATIONS:**

Slip grade for mono and co-extruded films for packaging.

#### **Regulatory Information**

Meets the requirements stipulated in standard IS: I0146 on "Specification for Polyethylene for safe use in contact
with foodstuffs, pharmaceuticals, and drinking water". It also conforms to the positive list of constituents as
prescribed in IS: 10141. The grade and the additives incorporated in it also comply with the FDA: CFR Title
21,177.1520, Olefin polymers.

#### **Storage Recommendations**

• Bags should be stored in dry/closed conditions at temperatures below 50°C and protected from UV / direct sunlight.

Reliance Industries Limited, Product Application & Research Center (PARC)
RIL Baroda Complex, P. O. Petrochemicals, Vadodara 391346, Gujrat. Tel.: +91-265-6696000. E-mail: polymer\_patsupport@ril.com Website: <a href="https://www.ril.com">www.ril.com</a>

The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or other wise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.

<sup>\*\*</sup> Typical value (Mechanical) with 40 μ film made with 0.7 mm die gap & 2.0 BUR