

HOPELEN SJ-150

PP HOMOPOLYMER

General Information

Description

SJ-150 is homo polymer resin produced through the polymerization of propylene. This grade is designed to be processed in conventional Injection molding equipment. SJ-150 shows good thermal stability and has high strength and stiffness. It is typically used in production of housewares and the general supplies.

Applications

- ◆Housewares and general supplies

Physical Properties¹

Physical	Test Method	Nominal Values			
Melt Flow Index	ASTM D1238	10	g/10min		
Density	ASTM D792	0.90	g/cm³		
Mechanical					
Tensile Stress (Yield)	ASTM D638	350	kgf/cm²	34	MPa
Tensile Strain (Break)	ASTM D638	>100	%	>100	%
Flexural Modulus	ASTM D790	15,000	kgf/cm²	1,470	MPa
Impact					
Notched Izod Impact Strength (23℃)	ASTM D256	3.5	kgf-cm/cm	34	J/m
Notched Izod Impact Strength (-10℃)	ASTM D256	2.5	kgf-cm/cm	25	J/m
Thermal					
Heat Deflection Temperature (4.6kgf/cm²)	ASTM D648	105	℃		
Additional Properties					
Flammability	UL94	HB			

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications

HOPELEN SJ-150

PP HOMOPOLYMER

General Information

Description

SJ-150 is homo polymer resin produced through the polymerization of propylene. This grade is designed to be processed in conventional Injection molding equipment. SJ-150 shows good thermal stability and has high strength and stiffness. It is typically used in production of housewares and the general supplies.

Applications

- ◆ Housewares and general supplies

Physical Properties¹

Physical	Test Method	Nominal Values			
Melt Flow Index	ISO 1133	10	g/10min		
Density	ISO 1183	0.90	g/cm³		
Mechanical					
Tensile Stress (Yield)	ISO 527-1	330	kgf/cm²	32	MPa
Tensile Strain (Break)	ISO 527-1	>100	%	>100	%
Flexural Modulus	ISO 178	12,000	kgf/cm²	1,180	MPa
Impact					
Notched Izod Impact Strength (23℃)	ISO 180	3.0	kgf-cm/cm	29	J/m
Notched Izod Impact Strength (-10℃)	ISO 180	2.0	kgf-cm/cm	20	J/m
Thermal					
Heat Deflection Temperature (4.6kgf/cm²)	ISO 75-1	85	℃		
Additional Properties					
Flammability	UL94	HB			

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications